

**Industrial index for rock gold mine DZ/T0208-2002)**

Type	Cut-off grade (10 <sup>-6</sup> )	Minimum Industrial Grade(10 <sup>-6</sup> )	The average grade of ore deposit (10 <sup>-6</sup> )	Minimum mining thickness(m)	Rock excluding thickness(m)	Excluding non-ore block thickness
Primary ore	1~2	2.5~4.5	4.5~5.5	Steep 0.8 Decantation 1.5	Underground mining 2 Open-pit mining 4	Corresponding Engineering 10~15 Non 20~30
Heap leaching chlorine onoxide	0.5~1	1~1.5				